

## Decorative Aluminum Anti-Graffiti Test

Graffiti resistance of decorative coating applied on aluminum



- Sample coated with a cycle 8 base and after then decorated
  - Marked with a black indelible pen type Pentel Pen N50
  - After 48 hours the sample is partially cleaned by a mixture of 1:1 methyl ketone and denatured alcohol
- Sample coated with a cycle 7 base and after then decorated
  - Varnished with coachbuilder's paint through a spray cylinder
  - After 48 hours the sample is partially cleaned by a mixture of 1:1 methyl ketone and denatured alcohol