

Decorative Aluminum Natural Exposure Test

Effects of natural exposure on decorative coating applied on aluminum



Sample #136

- Base: Protek Powder
- Decoration: Protek film 9061/401
- Exposure beginning: 10/4/01
- End of exposure: 10/4/02
- Thickness: 61 microns

- Gloss level at beginning: 18.4
- Gloss level at end: 17

Remaining gloss: 92%

Sample #207

- Base: **Non-Protek Powder**
- Decoration: Protek film 9061/401
- Exposure beginning: 10/4/01
- End of exposure: 10/4/02
- Thickness: 67 microns

- Gloss level at beginning: 21.6
- Gloss level at end: 5.9

Remaining gloss: 27%